

LUKO-edge finishing for Eternit façade panel Natura



- LUKO-paint bucket for maximum 0,5 l paint.
- Pot with 0,5 l LUKO-impregnation agent.  
(best before: 6 month after date of filling)
- LUKO is a dispersion, shake or stir well before use.
- Applicator with a special micro fibre-sponge (5 x 8 cm).



- Dip applicator in the impregnation agent.
- LUKO-impregnation agent is used undiluted.
- Wipe the applicator on the surface of the paint bucket to prevent dripping and to make sure that unnecessary dispersion can flow back.
- Processing temperature should be between +5°C and +25 °C.
- Storage temperature should be between -10°C and +25 °C.



- Finishing must be done sheet by sheet and not a stack all at once.
- Pull applicator in a small inclination along the edge, to avoid residues on the visible side.
- Impregnation running on top has to be wiped off immediately with a cloth in direction of the edge. Soiling on the surface has to be removed immediately.
- Never pour back surplus LUKO-edge impregnation out of the paint bucket into the pot, or use it later on.  
Replace impregnation agent approx. 200 cuts.
- The complete impregnation of the edges, of the Natura panel, prevents moisture absorption along the edges and any resulting temporary dark discolouring of the visible surface at the edges.



- LUKO-edge impregnation has to cover the saw cut completely.  
A sufficient impregnation can be recognized at the complete glossy surface of the edges.
- Thick and dry rest can be disposed in the normal garbage.  
After an immediate cleaning the sponge can be reused.